Research Article

Titanium Hydride Nanoplates Enable 5wt% of Reversible Hydrogen Storage by Sodium Alanate below 80°C

Zhuanghe Ren,¹ Xin Zhang,¹ Hai-Wen Li,² Zhenguo Huang,³ Jianjiang Hu ⁴,
Mingxia Gao,¹ Hongge Pan ^{1,5} and Yongfeng Liu ^{1,5}

¹State Key Laboratory of Silicon Materials and School of Materials Science and Engineering, Zhejiang University, Hangzhou 310027, China

²Hefei General Machinery Research Institute, Hefei 230031, China

³School of Civil & Environmental Engineering, University of Technology Sydney, 81 Broadway, Ultimo, NSW 2007, Australia

⁴School of Chemistry and Chemical Engineering, Yantai University, Yantai 264005, China

⁵Institute of Science and Technology for New Energy, Xi'an Technological University, Xi'an 710021, China

Correspondence should be addressed to Jianjiang Hu; jjj_hu@163.com, Hongge Pan; hgpan@zju.edu.cn, and Yongfeng Liu; mselyf@zju.edu.cn

Received 26 September 2021; Accepted 18 November 2021; Published 14 December 2021

Copyright © 2021 Zhuanghe Ren et al. Exclusive Licensee Science and Technology Review Publishing House. Distributed under a Creative Commons Attribution License (CC BY 4.0).

Sodium alanate (NaAlH_4) with 5.6 wt% of hydrogen capacity suffers seriously from the sluggish kinetics for reversible hydrogen storage. Ti-based dopants such as TiCl_4 , TiCl_3 , TiF_3 , and TiO_2 are prominent in enhancing the dehydrogenation kinetics and hence reducing the operation temperature. The tradeoff, however, is a considerable decrease of the reversible hydrogen capacity, which largely lowers the practical value of NaAlH_4 . Here, we successfully synthesized a new Ti-dopant, i.e., TiH_2 as nanoplates with ~50 nm in lateral size and ~15 nm in thickness by an ultrasound-driven metathesis reaction between TiCl_4 and LiH in THF with graphene as supports (denoted as NP- TiH_2 @G). Doping of 7 wt% NP- TiH_2 @G enables a full dehydrogenation of NaAlH_4 at 80°C and rehydrogenation at 30°C under 100 atm H_2 with a reversible hydrogen capacity of 5 wt%, superior to all literature results reported so far. This indicates that nanostructured TiH_2 is much more effective than Ti-dopants in improving the hydrogen storage performance of NaAlH_4 . Our finding not only pushes the practical application of NaAlH_4 forward greatly but also opens up new opportunities to tailor the kinetics with the minimal capacity loss.

1. Introduction

Hydrogen storage, bridging hydrogen generation and hydrogen application, plays a crucial role in a future hydrogen energy society [1–4]. Distinct from the matured technologies of compressed and liquefied hydrogen, solid state hydrides can realize higher hydrogen density under moderate pressures and temperature. Metal complex hydrides have attracted tremendous attention as the most promising hydrogen storage candidates because of their high gravimetric and volumetric hydrogen densities [5–8]. Sodium alanate, NaAlH_4 , is a typical complex hydride possessing 7.4 wt% of hydrogen capacity and favorable thermodynamics [9–12]. However, the sluggish kinetics results in high operation temperature and poor reversibility for hydrogen

storage in NaAlH_4 , therefore limiting its practical on-board applications.

Catalyst doping has been proved a feasible approach to help reducing the kinetic barriers of hydrogen storage reactions in metal hydrides. Transition metals and their compounds, especially Ti-based dopants, were found to have the ability to promote fast dissociation and recombination of hydrogen molecules [12–14]. In this respect, Bogdanović and Schwickardi contributed an important breakthrough by introducing a few millimoles of $\text{Ti}(\text{OBu})_4$ or TiCl_3 into NaAlH_4 , which enabled reversible hydrogen storage with NaAlH_4 at moderate conditions [15]. After that, a variety of Ti-based species have been explored and evaluated, including halides, oxides, nitrides, borides, carbides, hydrides, alloys, and elemental metals (Figure 1) [16–31]. In most cases, the

FIGURE 2: Schematic illustration for the preparation process of TiH_2 nanoplates.

and lithium hydride (LiH) along with a certain amount of graphene were added to tetrahydrofuran (THF) solution. Subsequently, the sonochemical process was conducted for 4 h at 40 kHz with continuous stirring. Finally, the solid-state product was obtained after filtrating, washing, and drying.

Only a broad diffraction peak at around 25° with high background was observed in the X-ray diffraction (XRD) profile (Figure 3(a)), suggesting that the solid-state product was in amorphous or nanocrystalline state. Energy dispersive spectroscopy (EDS) analysis revealed that it was mainly composed of Ti and C in addition to a traced amount of Cl and O as impurities (Figure 3(b)). Further Raman characterization indicated that the C signal could reasonably be attributed to graphene from the characteristic D-band and G-band at 1340 and 1590 cm^{-1} , respectively (Figure S1, Supporting Information). More importantly, H_2 emission was detected by mass spectroscopy (MS) while heating the solid-state product (Figure 3(c)). A sample in the absence of graphene was prepared according to reaction (1) with the same process to determine exactly the H content. Thermogravimetric analysis (TGA) results indicated around 4 wt% of weight loss (Figure 3(d)), agreeing well with the H content in TiH_2 . It is worth noting that the peak temperature for the hydrogen release of the solid product is around 120°C (Figure 3(c)), much lower than that of TiH_2 in microscale ($>500^\circ\text{C}$) [44]. Suggesting the successful synthesis of nanosized TiH_2 . Furthermore, the generation of H_2 as a gaseous product (Figure S2, Supporting Information) and the formation of LiCl in the filtrate (Figure S3, Supporting Information) as byproducts of reaction (1) were confirmed in the sonochemical process. Thus, the resultant solid-state product consisted of nanosized TiH_2 and graphene.

Figure 4 shows the morphology of the prepared TiH_2 . As shown in Figure 4(a), a large number of black nanoplates with $\sim 50\text{ nm}$ of average size dispersed on graphene can be observed from the transmission electron microscope (TEM) image. EDS mapping indicated that these nanoplates were mainly composed of Ti and C elements (Figure 4(b)). High-resolution TEM (HRTEM) clearly presents the fringes

of interplanar spacing of 0.21 nm (Figure 4(c)), which corresponds to the (002) planes of TiH_2 . The TEM observations, therefore, strongly prove the successful synthesis of graphene-supported TiH_2 nanoplates (denoted as NP- $\text{TiH}_2@\text{G}$ hereinafter) by a newly developed sonochemical process. The thickness of the prepared TiH_2 nanoplates was determined as $\sim 15\text{ nm}$ by atomic force microscope (AFM) measurement (Figure 4(d)).

A time dependence of growth of TiH_2 nanoplates was also clearly observed by means of TEM (as shown in Figure 5). For comparison, the pristine graphene with a clean surface is shown in Figure S4 (Supporting Information). After 1 h of ultrasonic treatment, a large number of $\sim 10\text{ nm}$ sized black sheets cover on the graphene (Figures 5(a) and 5(b)). Extending the time to 2 h, some nanoplates grew up to $\sim 50\text{ nm}$ (Figures 5(c) and 5(d)). Further extending to 4 h, the $\sim 50\text{ nm}$ -sized nanoplates were largely increased in quantity along with the disappearance of small nanosheets (Figures 5(e) and 5(f)). The loading amount of TiH_2 was determined to be $\sim 70\%$ in weight by inductively coupled plasma spectroscopy (ICP) examination, which is distinctly higher than that obtained previously by a solvothermal process ($\sim 46\%$) [44]. Thus, higher catalytic activity was expected. In a strong contrast, only coarse particles with $\sim 500\text{ nm}$ in size were obtained via the same sonochemical process without graphene as support (Figure S5, Supporting Information). This fact unambiguously indicates the critical important role played by graphene as a hard template governing the morphology of TiH_2 nanoplate, attributed to the very similarity in lattice spacings ($2.10\text{ \AA}$ for the (002) planes of TiH_2 and $2.13\text{ \AA}$ for the (100) planes of graphene) [44].

2.2. Catalytic Activity of TiH_2 Nanoplates. The 4 h-sonicated NP- $\text{TiH}_2@\text{G}$ was selected to mix with NaAlH_4 by ball milling in order to evaluate its catalytic effectiveness because it took 4 h to complete the conversion of TiH_2 from TiCl_4 as indicated by the thorough disappearance of the characteristic reflections of LiH in the XRD profile after 4 h of sonification (Figure S6, Supporting Information). Six samples of

FIGURE 3: (a) XRD pattern, (b) EDS spectrum, (c) TPD-MS signal, and (d) TGA curve of as-prepared solid products of the sonochemical reaction between TiCl_4 and LiH in THF.

NaAlH_4 - $x\text{NP-TiH}_2$ @G with $x = 0, 1, 3, 5, 7$, and $9\text{ wt\%}$ were examined. A remarkable reduction in the dehydrogenation temperature of NaAlH_4 was observed as NP-TiH_2 @G increasing from $1\text{ wt\%}$ to $7\text{ wt\%}$ (as shown in Figure 6(a)). For the $7\text{ wt\%}$ NP-TiH_2 @G-containing sample, the release of hydrogen started from 80°C and completed at 160°C with an usable hydrogen capacity of $5\text{ wt\%}$. The on-set and end temperatures of dehydrogenation were reduced by 115 and 180°C , respectively, compared to those of the pristine NaAlH_4 . Further increase of NP-TiH_2 @G to $9\text{ wt\%}$ caused an obvious loss of hydrogen capacity without obvious reduction in the dehydrogenation temperature. Therefore, $7\text{ wt\%}$ was the optimal amount for NP-TiH_2 @G by taking into account of the hydrogen capacity and the dehydrogenation temperature.

The dehydrogenated sample was subsequently subjected to hydrogenation with ramped temperatures under 100 atm of H_2 pressure (as shown in Figure 6(b)). The $7\text{ wt\%}$ NP-TiH_2 @G-containing sample showed superior rehydrogenation

properties to those of pristine NaAlH_4 and NaAlH_4 doped with the commercial TiH_2 . Specifically, $7\text{ wt\%}$ NP-TiH_2 @G-containing sample absorbed $5\text{ wt\%}$ H_2 from 25°C to 105°C . It is worth emphasizing that the $7\text{ wt\%}$ NP-TiH_2 @G-containing sample started to absorb hydrogen at a temperature as low as 25°C , and more than 90% of the rehydrogenation can be completed below 90°C , which is close to the working temperature of PEMFC. Such significant improvement of the rehydrogenation by the addition of $7\text{ wt\%}$ NP-TiH_2 @G demonstrated for the first time that high reversible capacity coupled with the dehydrogenation temperature of NaAlH_4 can be achieved simultaneously by a proper dopant, which can be mainly attributed to the highly homogenous dispersion of the prepared NP-TiH_2 @G (Figure 6(c)) than that of the commercial TiH_2 (Figure 6(d)) in NaAlH_4 . The Ti-rich area was clearly observed in NaAlH_4 doped with the commercial TiH_2 , probably due to the large particle size of TiH_2 (Figure S7, Supporting Information). More importantly, most of the NP-TiH_2 was converted to

FIGURE 4: (a) TEM image, (b) EDS mapping, (c) HRTEM image, and (d) AFM image of NP-TiH₂@G. Inset on (a) is the corresponding particle size distribution.

Al-Ti species after 24 h ball milling with NaAlH₄, whereas only small amount of Al-Ti species can be detected in the commercial TiH₂ (Figure S8, Supporting Information). This suggests that the reduced particle size of TiH₂ facilitates the formation of Al-Ti species, which possess high catalytic activity for the dehydrogenation and rehydrogenation of NaAlH₄ [9, 34, 40]. Further XRD characterization indicated that the reversible hydrogen capacity still originated from the decomposition and reformation of NaAlH₄ (as shown in Figure S9 (Supporting Information)).

Moreover, the dehydrogenation temperature was further reduced by ~10°C in the follow-up 2nd cycle (Figure S10, Supporting Information). It can be clearly seen that the particle size of Ti-containing species reduced largely to around 5 nm from the aberration-corrected scanning transmission electron microscope (STEM) observation and EDS mapping analyses (as shown in Figure 7). From the relative content analyses, the Al-Ti species changed from Al₈₅Ti₁₅ for the as-milled sample to Al₅₈Ti₄₂ for the cycled sample, close to Al₅₀Ti₅₀, suggesting the reconstruction or optimization of the local atomic structure of Al-Ti species during cycling. This is further evidenced by the slight low-angle shift of the characteristic reflection of Al-Ti species in the XRD profiles because of the incorporation of more Ti (Figure S11, Supporting Information). According to the density functional theory (DFT) calculation, the kinetic barrier of the transfer of H atom from NaAlH₄ to the surface of Al is largely reduced from 0.47 eV (Figure S12a,

Supporting Information) to 0.14 eV (Figure S12b, Supporting Information) with the presence of one Ti atom. This process can even proceed spontaneously when two Ti atoms are introduced into the surface of Al in the near-nearest-neighbor mode (Figure S12c, Supporting Information). This suggests that the Al-Ti species are of great importance for the significant improvement of dehydrogenation kinetics of NaAlH₄, which agrees well with the previous reports [40, 45].

2.3. Hydrogen Storage Kinetics of NP-TiH₂@G-Containing NaAlH₄. Figures 8(a) and 8(b) show the isothermal dehydrogenation behaviors of NaAlH₄-7 wt% NP-TiH₂@G sample after 1 dehydrogenation/rehydrogenation cycle, measured by volumetric and thermogravimetric (TG) methods, respectively. Isothermal volumetric dehydrogenation indicates that the full dehydrogenation of 5 wt% of hydrogen was achieved within 30 min at 140°C. At 120°C, it took around 200 min to complete. Even at 100°C, the major part of hydrogen (around 3.2 wt%) can be released within 30 min and the dehydrogenation completed within 500 min. The time for the full dehydrogenation was reduced to only 250 min at TG measurement (Figure 8(b)), which is attributed to the absence of blocking effect from hydrogen back pressure. More encouragingly, the full dehydrogenation can be achieved even at 80°C, which is the lowest dehydrogenation temperature for NaAlH₄ reported so far.

The full isothermal rehydrogenation (~5 wt% of hydrogen) of dehydrogenated NaAlH₄-7 wt% NP-TiH₂@G completed within only 25 min at 100°C (as shown in

FIGURE 5: TEM images of NP-TiH₂@G with the ultrasonic time of 1 h (a, b), 2 h (c, d), and 4 h (e, f).

Figure 8(c)). Amazingly, the full rehydrogenation was also achieved even at 30°C. This is the first complex hydride system that is able to work at the target temperature range proposed by US DOE with 5 wt% of reversible hydrogen capacity, although the dehydrogenation/rehydrogenation rates need to be further improved [46].

The apparent activation energy of dehydrogenation reactions of NaAlH₄-7 wt% NP-TiH₂@G was calculated based on the Kissinger's plots (Figure 8(d)), in which the peak temperatures and the heating rates were obtained from temperature programmed desorption (TPD) curves shown in Figure S13 (Supporting Information). The apparent activation energies for each step are 80 ± 3.3 and 70 ± 2.8 kJ mol⁻¹, respectively. These values are reduced by ~40% compared to those of the pristine NaAlH₄ [47], and even remarkably lower than those of other catalyst-modified NaAlH₄ systems (Table S1) [48–54], indicating the significant reduction of the dehydrogenation kinetic

barriers induced by the newly formed Al-Ti catalytic species. In contrast, the addition of 7 wt% NP-TiH₂@G did not affect much the thermodynamic properties of NaAlH₄ as indicated by the nearly unchanged desorption enthalpy change, which were determined to be approximately 36.5/47.4 and 36.3/47.0 kJ/mol-H₂ for pristine sample and 7 wt% NP-TiH₂@G-containing sample, respectively, by analyzing the differential scanning calorimetry (DSC) results (Figure S14, Supporting Information).

2.4. Dehydrogenation/Rehydrogenation Cycling of NP-TiH₂@G-Containing NaAlH₄. Dehydrogenation/rehydrogenation cycling performance of the NaAlH₄-7 wt% NP-TiH₂@G sample is shown in Figure 9(a). Here, dehydrogenation was operated at 140°C under initial vacuum and rehydrogenation at 100°C/100 atm H₂. No obvious degradation was observed after 50 cycles. The hydrogen capacity was 4.8 wt% at the 50th cycle, which means a capacity retention

FIGURE 6: (a) Volumetric release curves of NaAlH₄ doped with NP-TiH₂@G, (b) nonisothermal hydrogenation curves, and (c, d) SEM and corresponding EDS mapping of NaAlH₄ mixed with 7 wt% (c) TiH₂ nanoplates and (d) commercial TiH₂.

of 96% based on the initial capacity of 5.0 wt%. The cycling performance demonstrates a stable cyclability of the NP-TiH₂@G-containing NaAlH₄.

To shed light on the stable cycling behavior of NP-TiH₂@G-containing NaAlH₄, the particle size, distribution, and chemical states of catalytic species were examined and analyzed. TEM observation displayed that the catalytic species remained as ultrafine particles of ~5 nm in size without obvious agglomeration (Figure 9(b)). EDS mapping analyses (Figures 9(c) and 9(d)) indicated the homogenous distribution of Ti element on NaAlH₄ matrix even after 50 cycles. In addition, high-resolution XPS spectra of Ti 2p showed a stable chemical state from 2 to 50 cycles for the nearly unchanged 2p_{3/2}-2p_{1/2} spin-orbit doublet at 453.2/458.1 eV (Figure 9(e)) [55]. As a result, we believe that the small particle size, homogenous dispersion, and stable chemical state are of critical importance for the long-term cyclability of NP-TiH₂@G-containing NaAlH₄. This finding provides important insights and greatly encourages the further devel-

opment of the catalysis-promoted complex hydrides for practical on-board applications.

3. Discussion

Two-dimensional TiH₂ nanoplates with a lateral size of 50 nm and a thickness of 15 nm were successfully synthesized by using graphene as support, based on a novel facile sonochemical process. The graphene played a critical role in the nucleation and growth of TiH₂ nanoplates. The prepared TiH₂ nanoplates displayed superior catalytic activity than the commercial TiH₂ of microscale for hydrogen storage in NaAlH₄. The 7 wt% NP-TiH₂@G-containing NaAlH₄ started releasing hydrogen at 80°C, which was lowered by 115°C in comparison with pristine sample. In TG measurement, full dehydrogenation was achieved with 5.0 wt% of practical hydrogen capacity even at 80°C. It is worth emphasizing that the rehydrogenation can complete at 30°C under 100 atm of H₂. Operating at 140°C/initial vacuum for

FIGURE 7: STEM and corresponding EDS mapping of as-milled (a) and activated (b) NaAlH_4 -7 wt% NP- TiH_2 @G samples. The rectangular areas in (a) and (b) are taken for composition analysis.

dehydrogenation and $100^\circ\text{C}/100\text{ atm H}_2$ for rehydrogenation, a stable cyclability was confirmed, as only 0.2 wt% of capacity loss after 50 cycles. Mechanistic studies revealed the active catalytic species was converted from TiH_2 to $\text{Al}_{85}\text{Ti}_{15}$ during ball milling and further to near $\text{Al}_{50}\text{Ti}_{50}$ after the first de-/hydrogenation cycle, which remained stable in the subsequent cycling. DFT calculations reveal that the kinetic barrier of the transfer of H atom from NaAlH_4 to the surface of Al is largely reduced by the formation of Al-Ti species. The small particle, homogenous dispersion and stable chemical state of active catalytic species are responsible for the long-term cyclability of NP- TiH_2 @G-containing NaAlH_4 . The findings presented in this work make NaAlH_4 step closer towards practical on-board hydrogen storage applications.

4. Materials and Methods

4.1. Materials Synthesis. All reagents and solvents were purchased and used as received without further purification. TiH_2 nanoplates supported on graphene (NP- TiH_2 @G) were synthesized by a newly developed sonochemical process [56] under argon atmosphere using titanium chloride (TiCl_4 , 99.9%, Aladdin), lithium hydride (LiH, 99.4%, Alfa Aesar), and graphene (97%, Aladdin) as the raw materials. In a typical procedure, TiCl_4 (2 mmol), LiH (8 mmol), and graphene (20 mg) were sequentially added to 70 mL THF in a flask-3-neck which was irradiated by ultrasonic waves (40 kHz, W-600D, Shanghai Ultrasonic Instrument, Shanghai, China) for 4 h under mechanical stirring. A black precipitate of NP- TiH_2 @G was separated from the THF solution by filtration, washed twice with THF and finally dried at 70°C under dynamic vacuum. The obtained NP- TiH_2 @G was mixed with NaAlH_4 on a planetary ball mill (Nanjing, China). The ball milling was conducted at 500 rpm for 24 h in the

milling jar filled with 50 atm H_2 at the ball-to-sample weight ratio of approximately 120:1. The doping amounts of NP- TiH_2 @G were set to be $x = 0, 1, 3, 5, 7$, and 9 wt%.

4.2. Characterization. The structure information was collected on a MiniFlex 600 X-ray diffractometer (XRD) (Rigaku, Japan) with $\text{Cu K}\alpha$ radiation ($\lambda = 0.15406\text{ nm}$) operated at 40 kV and 15 mA. The 2θ range was set at 10 – 90° with a 0.05° step increment. A custom-designed container with a window covered by Scotch tape was used to prevent air and moisture exposure of the sample. The sample morphology and microstructure were observed with scanning electron microscope (SEM) (Hitachi S-4800), aberration-corrected scanning transmission electron microscope (STEM) (Titan G² 80-200 Chemi STEM FEI, 200 kV), and TEM (Tecnai G² F20 S-TWIN FEI, 200 kV). For SEM observation, the sample was transferred quickly to the SEM facility under Ar protection. For STEM and TEM examinations, the sample was protected with a double-tilt vacuum transfer holder (Gatan 648, USA). Atomic force microscope (AFM) characterization was performed on Bruker Dimension Icon under the tapping mode, with samples prepared by dropping freshly diluted sample solutions onto silicon substrates. X-ray photoelectron spectroscopy (XPS) analyses were carried out using a Thermo Scientific ESCALAB 250Xi spectrometer with a monochromatic Al K α X-ray source at a base pressure of 6.8×10^{-9} Torr. The Ti content of samples were determined by inductively coupled plasma (ICP) spectroscopy on a PE Optima 8000 instrument.

4.3. Property Measurements. A home-built temperature programmed desorption (TPD) system attached to a mass spectrometer (MS) was employed to characterize the temperature-dependent dehydrogenation behavior using Ar

FIGURE 8: (a) Isothermal dehydrogenation curves, (b) isothermal TG curves, (c) isothermal hydrogenation curves, and (d) Kissinger's plots of activated NaAlH₄-7 wt% NP-TiH₂@G sample.

as a carrier gas with a flow rate of 20 mL min⁻¹. For each test, approximately 40 mg sample was heated up from room temperature to desired temperatures at 2°C min⁻¹. Quantitative dehydrogenation/hydrogenation properties were measured using a Sieverts-type apparatus under isothermal and nonisothermal conditions, and the sample loading was approximately 70 mg sample. The nonisothermal data were acquired by gradually heating the sample from room temperature to a preset temperature at an average rate of 2°C min⁻¹ under primary vacuum (-10^{-3} Torr) for dehydrogenation and 1°C min⁻¹ with 100 atm H₂ for hydrogenation. The isothermal measurements were conducted by rapidly heating the sample to a desired temperature and then dwelling during the entire test. The temperature and pressure

were monitored and recorded simultaneously, and the amounts of hydrogen released/uptaken were calculated based upon the ideal gas law. Thermogravimetric analysis (TGA) was carried out on a Netzsch TG 209 F3 instrument under an argon atmosphere at a ramping rate of 2°C min⁻¹. Differential scanning calorimetry (DSC) experiments were performed with a NETZSCH DSC 200F3 unit at 2°C min⁻¹ of heating rate. Approximately 2 mg of sample was placed in an Al₂O₃ crucible for measurement.

4.4. Theoretical Calculation. Density functional theory (DFT) calculations were conducted in the Vienna Ab initio Simulation Package (VASP). The generalized gradient approximation (GGA) with Perdew-Burke-Ernzerhof (PBE)

FIGURE 9: (a) Cycling tests operated at 140°C for dehydrogenation and 100°C/100 atm H_2 for hydrogenation of $NaAlH_4$ -7 wt% NP- $TiH_2@G$, (b) TEM image, (c) STEM and corresponding EDS mapping images, (d) SEM and corresponding images, and (e) Ti 2p XPS spectra of $NaAlH_4$ -7 wt% NP- $TiH_2@G$ sample after 50 cycles.

model was taken as the exchange-correlation functional [57]. Projector augmented wave pseudopotentials (PAWs) were employed to model the ionic potentials [58]. The precession setting of “PREC = Accurate” was used. All atoms were fully

relaxed until the force on them was less than $0.05 \text{ eV } \text{\AA}^{-1}$. The Brillouin zone integration was performed with gamma-centred sampling of $3 \times 3 \times 1$. The minimum-energy pathway was computed using the climbing-image nudged elastic

band (CI-NEB) method [59]. Al(111) surface was selected because it has the lowest surface free energy and then is most likely exposed. A six-layer slab containing 96 atoms was constructed to simulate the surface with the lowest two layers fixed to represent the bulk. The thickness of vacuum layer was set as 20 Å to avoid interaction between neighbouring images.

Data Availability

The data used to support the findings of this study are included within the article and supplementary information files and/or may be requested from the authors.

Conflicts of Interest

The authors declare no competing financial interest.

Authors' Contributions

Z.H.R. and X.Z. contributed equally to this work.

Acknowledgments

We gratefully acknowledge the financial support received from the Natural Science Foundation of Zhejiang Province (LD21E010002), the National Outstanding Youth Foundation of China (52125104), the National Natural Science Foundation of China (52071285 and 52001277), the National Key R&D Program of China (2018YFB1502102), the Fundamental Research Funds for the Central Universities (2021FZZX001-09), and the National Youth Top-Notch Talent Support Program.

Supplementary Materials

Figure S1: Raman spectrum of as-prepared solid product after sonochemical reaction between TiCl_4 and LiH in THF. Figure S2: MS signal of gaseous product of reaction of TiCl_4 with LiH in THF under ultrasonic treatment. Figure S3: XRD profile of the solid obtained by drying the filtrate of reaction of TiCl_4 with LiH in THF under ultrasonic treatment. Figure S4: TEM image of pristine graphene. Figure S5: SEM image of TiH_2 prepared by sonochemical reaction of TiCl_4 and LiH without graphene as support. Figure S6: XRD profiles of NaAlH_4 doped by 7 wt% $\text{NF-TiH}_2@\text{G}$ prepared by different ultrasonic times. Figure S7: SEM image of commercial TiH_2 . Figure S8: Ti 2p XPS spectra of NaAlH_4 mixed with commercial TiH_2 and TiH_2 nanoplates. Figure S9: XRD profiles of 7 wt% $\text{NF-TiH}_2@\text{G}$ -containing NaAlH_4 after different treatments. Figure S10: the volumetric dehydrogenation curves of activated NaAlH_4 -7 wt% $\text{NP-TiH}_2@\text{G}$ sample. Figure S11: XRD profiles of NaAlH_4 -7 wt% $\text{NP-TiH}_2@\text{G}$ sample after ball milling and 1st de/rehydrogenation cycle (2θ : 39–44°). Figure S12: energy barriers of H atom transferring from NaAlH_4 molecule to Al surface (a) and single-Ti-substituted Al surface (b) and relaxed geometry of NaAlH_4 molecule placed on two-Ti-substituted Al surface (c). Figure S13: TPD curves of activated NaAlH_4 -7 wt% $\text{NP-TiH}_2@\text{G}$ sample with different

heating rates. Figure S14: DSC curves of pristine NaAlH_4 and NaAlH_4 -7 wt% $\text{NP-TiH}_2@\text{G}$ samples. Table S1: comparison of activation energy (E_a) of NaAlH_4 doped with different catalysts. (*Supplementary Materials*)

References

- [1] L. Schlapbach and A. Züttel, "Hydrogen-storage materials for mobile applications," *Nature*, vol. 414, no. 6861, pp. 353–358, 2001.
- [2] J. Zheng, C.-G. Wang, H. Zhou et al., "Current research trends and perspectives on solid-state nanomaterials in hydrogen storage," *Research*, vol. 2021, article 3750689, 39 pages, 2021.
- [3] C. G. Lang, Y. Jia, and X. Yao, "Recent advances in liquid-phase chemical hydrogen storage," *Energy Storage Materials*, vol. 26, pp. 290–312, 2020.
- [4] T. He, P. Pachfule, H. Wu, Q. Xu, and P. Chen, "Hydrogen carriers," *Nature Reviews Materials*, vol. 1, no. 12, article 16067, 2016.
- [5] S.-I. Orimo, Y. Nakamori, J. R. Eliseo, A. Züttel, and C. M. Jensen, "Complex hydrides for hydrogen storage," *Chemical Reviews*, vol. 107, no. 10, pp. 4111–4132, 2007.
- [6] L. Z. Ouyang, K. Chen, J. Jiang, X. S. Yang, and M. Zhu, "Hydrogen storage in light-metal based systems: a review," *Journal of Alloys and Compounds*, vol. 829, article 154597, 2020.
- [7] L. Li, Y. Huang, C. An, and Y. Wang, "Lightweight hydrides nanocomposites for hydrogen storage: challenges, progress and prospects," *Science China Materials*, vol. 62, no. 11, pp. 1597–1625, 2019.
- [8] X. B. Yu, Z. Tang, D. Sun, L. Ouyang, and M. Zhu, "Recent advances and remaining challenges of nanostructured materials for hydrogen storage applications," *Progress in Materials Science*, vol. 88, pp. 1–48, 2017.
- [9] T. J. Frankcombe, "Proposed mechanisms for the catalytic activity of Ti in NaAlH_4 ," *Chemical Reviews*, vol. 112, no. 4, pp. 2164–2178, 2012.
- [10] B. Bogdanović, M. Felderhoff, A. Pommerin, F. Schüth, and N. Spielkamp, "Advanced hydrogen-storage materials based on Sc-, Ce-, and Pr-doped NaAlH_4 ," *Advanced Materials*, vol. 18, no. 9, pp. 1198–1201, 2006.
- [11] N. A. Ali and M. Ismail, "Modification of NaAlH_4 properties using catalysts for solid-state hydrogen storage: a review," *International Journal of Hydrogen Energy*, vol. 46, no. 1, pp. 766–782, 2021.
- [12] Y. F. Liu, Z. H. Ren, X. Zhang et al., "Development of catalyst-enhanced sodium alanate as an advanced hydrogen-storage material for mobile applications," *Energy Technology*, vol. 6, no. 3, pp. 487–500, 2018.
- [13] X. L. Zhang, Y. F. Liu, X. Zhang, J. J. Hu, M. X. Gao, and H. G. Pan, "Empowering hydrogen storage performance of MgH_2 by nanoengineering and nanocatalysis," *Materials Today Nano*, vol. 9, article 100064, 2020.
- [14] W. X. Zhang, X. Zhang, Z. G. Huang et al., "Recent development of lithium borohydride-based materials for hydrogen storage," *Advanced Energy and Sustainability Research*, vol. 2, no. 10, article 2100073, 2021.
- [15] B. Bogdanović and M. Schwickardi, "Ti-doped alkali metal aluminium hydrides as potential novel reversible hydrogen

- storage materials¹,” *Journal of Alloys and Compounds*, vol. 253–254, pp. 1–9, 1997.
- [16] G. Lee, J. Shim, Y. Cho, and K. Lee, “Improvement in desorption kinetics of NaAlH₄ catalyzed with TiO₂ nanopowder,” *International Journal of Hydrogen Energy*, vol. 33, no. 14, pp. 3748–3753, 2008.
 - [17] N. Eigen, M. Kunowsky, T. Klassen, and R. Bormann, “Synthesis of NaAlH₄-based hydrogen storage material using milling under low pressure hydrogen atmosphere,” *Journal of Alloys and Compounds*, vol. 430, no. 1–2, pp. 350–355, 2007.
 - [18] X. Z. Xiao, K. R. Yu, X. L. Fan et al., “Synthesis and hydriding/dehydriding properties of nanosized sodium alanates prepared by reactive ball-milling,” *International Journal of Hydrogen Energy*, vol. 36, no. 1, pp. 539–548, 2011.
 - [19] G. D. Zou, B. Z. Liu, J. X. Guo, Q. Zhang, C. Fernandez, and Q. Peng, “Synthesis of nanoflower-shaped Mxene derivative with unexpected catalytic activity for dehydrogenation of sodium alanates,” *ACS Applied Materials & Interfaces*, vol. 9, no. 8, pp. 7611–7618, 2017.
 - [20] X. Z. Xiao, X. L. Fan, K. R. Yu et al., “Catalytic mechanism of new TiC-doped sodium alanate for hydrogen storage,” *Journal of Physical Chemistry C*, vol. 113, no. 48, pp. 20745–20751, 2009.
 - [21] Z. L. Yuan, D. F. Zhang, G. X. Fan, Y. Chen, Y. Fan, and B. Liu, “Synergistic effect of CeF₃ Nanoparticles supported on Ti₃C₂ MXene for catalyzing hydrogen storage of NaAlH₄,” *ACS Applied Energy Materials*, vol. 4, no. 3, pp. 2820–2827, 2021.
 - [22] R. C. Jiang, X. Xiao, J. Zheng, M. Chen, and L. Chen, “Remarkable hydrogen absorption/desorption behaviors and mechanism of sodium alanates in-situ doped with Ti-based 2D Mxene,” *Materials Chemistry and Physics*, vol. 242, article 122529, 2020.
 - [23] J. W. Kim, J.-H. Shim, S. C. Kim et al., “Catalytic effect of titanium nitride nanopowder on hydrogen desorption properties of NaAlH₄ and its stability in NaAlH₄,” *Journal of Power Sources*, vol. 192, no. 2, pp. 582–587, 2009.
 - [24] L. Li, F. Qiu, Y. Wang et al., “Tin catalyst for the reversible hydrogen storage performance of sodium alanate system,” *Journal of Materials Chemistry*, vol. 22, no. 27, p. 13782, 2012.
 - [25] L. Li, F. Y. Qiu, Y. J. Wang et al., “Crystalline TiB₂: an efficient catalyst for synthesis and hydrogen desorption/absorption performances of NaAlH₄ system,” *Journal of Materials Chemistry*, vol. 22, no. 7, pp. 3127–3132, 2012.
 - [26] X. Xiao, L. Chen, X. Wang, S. Li, C. Chen, and Q. Wang, “Reversible hydrogen storage properties and favorable co-doping mechanism of the metallic Ti and Zr co-doped sodium aluminum hydride,” *International Journal of Hydrogen Energy*, vol. 33, no. 1, pp. 64–73, 2008.
 - [27] P. Wang and C. M. Jensen, “Preparation of Ti-doped sodium aluminum hydride from mechanical milling of NaH/Al with off-the-shelf Ti powder,” *Journal of Physical Chemistry B*, vol. 108, no. 40, pp. 15827–15829, 2004.
 - [28] M. P. Pitt, P. E. Vullum, M. H. Sørby et al., “Hydrogen absorption kinetics and structural features of NaAlH₄ enhanced with transition-metal and Ti-based nanoparticles,” *International Journal of Hydrogen Energy*, vol. 37, no. 20, pp. 15175–15186, 2012.
 - [29] X. Zhang, X. L. Zhang, Z. H. Ren et al., “Amorphous-carbon-supported ultrasmall TiB₂ nanoparticles with high catalytic activity for reversible hydrogen storage in NaAlH₄,” *Frontiers in Chemistry*, vol. 8, article 419, 2020.
 - [30] X. Zhang, Z. H. Ren, Y. H. Lu et al., “Facile synthesis and superior catalytic activity of nano-TiN@N-C for hydrogen storage in NaAlH₄,” *ACS Applied Materials & Interfaces*, vol. 10, no. 18, pp. 15767–15777, 2018.
 - [31] R. Y. Wu, H. du, Z. Y. Wang, M. Gao, H. Pan, and Y. Liu, “Remarkably improved hydrogen storage properties of NaAlH₄ doped with 2D titanium carbide,” *Journal of Power Sources*, vol. 327, pp. 519–525, 2016.
 - [32] F. Schüth, B. Bogdanović, and M. Felderhoff, “Light metal hydrides and complex hydrides for hydrogen storage,” *Chemical Communications*, vol. 20, pp. 2249–2258, 2004.
 - [33] S. Zhang, C. Lu, N. Takeichi, T. Kiyobayashi, and N. Kuriyama, “Reaction stoichiometry between TiCl₃ and NaAlH₄ in Ti-doped alanate for hydrogen storage: the fate of the titanium species,” *International Journal of Hydrogen Energy*, vol. 36, no. 1, pp. 634–638, 2011.
 - [34] A. Léon, D. Schild, and M. Fichtner, “Chemical state of Ti in sodium alanate doped with TiCl₃ using X-ray photoelectron spectroscopy,” *Journal of Alloys and Compounds*, vol. 404–406, pp. 766–770, 2005.
 - [35] P. Wang, X. D. Kang, and H. M. Cheng, “Improved hydrogen storage of TiF₃-Doped NaAlH₄,” *ChemPhysChem*, vol. 6, no. 12, pp. 2488–2491, 2005.
 - [36] L. Li, F. Y. Qiu, Y. J. Wang et al., “Improved dehydrogenation performances of TiB₂-doped sodium alanate,” *Materials Chemistry and Physics*, vol. 134, no. 2–3, pp. 1197–1202, 2012.
 - [37] T. Wang, J. Wang, A. D. Ebner, and J. A. Ritter, “Reversible hydrogen storage properties of NaAlH₄ catalyzed with scandium,” *Journal of Alloys and Compounds*, vol. 450, no. 1–2, pp. 293–300, 2008.
 - [38] K. J. Gross, E. H. Majzoub, and S. W. Spangler, “The effects of titanium precursors on hydriding properties of alanates,” *Journal of Alloys and Compounds*, vol. 356–357, pp. 423–428, 2003.
 - [39] X. Kang, P. Wang, and H. Cheng, “In situ formation of Ti hydride and its catalytic effect in doped NaAlH₄ prepared by milling NaH/Al with metallic Ti powder,” *International Journal of Hydrogen Energy*, vol. 32, no. 14, pp. 2943–2948, 2007.
 - [40] X. Zhang, Y. Liu, K. Wang, M. Gao, and H. Pan, “Remarkably improved hydrogen storage properties of nanocrystalline TiO₂-modified NaAlH₄ and evolution of Ti-containing species during dehydrogenation/hydrogenation,” *Nano Research*, vol. 8, no. 2, pp. 533–545, 2015.
 - [41] G. K. P. Dathara and D. S. Mainardi, “Structure and dynamics of Ti–Al–H compounds in Ti-doped NaAlH₄,” *Molecular Simulation*, vol. 34, no. 2, pp. 201–210, 2008.
 - [42] G. K. P. Dathar and D. S. Mainardi, “Kinetics of hydrogen desorption in NaAlH₄ and Ti-containing NaAlH₄,” *Journal of Physical Chemistry C*, vol. 114, no. 17, pp. 8026–8031, 2010.
 - [43] J. Íñiguez and T. Yildirim, “First-principles study of Ti-doped sodium alanate surfaces,” *Applied Physics Letters*, vol. 86, no. 10, article 103109, 2005.
 - [44] Z. H. Ren, X. Zhang, Z. G. Huang et al., “Controllable synthesis of 2D TiH₂ nanoflakes with superior catalytic activity for low-temperature hydrogen cycling of NaAlH₄,” *Chemical Engineering Journal*, vol. 427, article 131546, 2022.
 - [45] X. Zhang, Z. H. Ren, X. L. Zhang, M. Gao, H. Pan, and Y. Liu, “Triggering highly stable catalytic activity of metallic titanium for hydrogen storage in NaAlH₄ by preparing ultrafine nanoparticles,” *Journal of Materials Chemistry A*, vol. 7, no. 9, pp. 4651–4659, 2019.

- [46] US Department of Energy, "DOE Technical Targets for Onboard Hydrogen Storage for Light-Duty Vehicles," US Washington DC, 2016 <https://www.energy.gov/eere/fuelcells/doe-technical-targets-onboard-hydrogen-storage-light-duty-vehicles>.
- [47] X. Zhang, R. Y. Wu, Z. Y. Wang, M. Gao, H. Pan, and Y. Liu, "Preparation and catalytic activity of a novel nanocrystalline $\text{ZrO}_2\text{@C}$ composite for hydrogen storage in NaAlH_4 ," *Chemistry-An Asian Journal*, vol. 11, no. 24, pp. 3541–3549, 2016.
- [48] Y. F. Liu, C. Liang, H. Zhou, M. Gao, H. Pan, and Q. Wang, "A novel catalyst precursor K_2TiF_6 with remarkable synergetic effects of K, Ti and F together on reversible hydrogen storage of NaAlH_4 ," *Chemical Communications*, vol. 47, no. 6, pp. 1740–1742, 2011.
- [49] L. Li, Y. Wang, F. Y. Qiu et al., "Reversible hydrogen storage properties of NaAlH_4 enhanced with TiN catalyst," *Journal of Alloys and Compounds*, vol. 566, pp. 137–141, 2013.
- [50] N. H. Idris, A. S. K. Anuar, N. A. Ali, and M. Ismail, "Effect of K_2NbF_7 on the hydrogen release behaviour of NaAlH_4 ," *Journal of Alloys and Compounds*, vol. 851, article 156686, 2021.
- [51] J. F. Mao, Z. Guo, and H. Liu, "Improved hydrogen sorption performance of NbF_5 -catalysed NaAlH_4 ," *International Journal of Hydrogen Energy*, vol. 36, no. 22, pp. 14503–14511, 2011.
- [52] N. S. Mustafa, M. S. Yahya, N. Sazelee, N. A. Ali, and M. Ismail, "Dehydrogenation properties and catalytic mechanism of the K_2NiF_6 -doped NaAlH_4 System," *ACS Omega*, vol. 3, no. 12, pp. 17100–17107, 2018.
- [53] N. Sazelee, N. S. Mustafa, M. S. Yahya, and M. Ismail, "Enhanced dehydrogenation performance of NaAlH_4 by the addition of spherical SrTiO_3 ," *International Journal of Energy Research*, vol. 45, no. 6, pp. 8648–8658, 2021.
- [54] X. L. Fan, X. Z. Xiao, L. X. Chen et al., "Hydriding-dehydriding kinetics and the microstructure of La- and Sm-doped NaAlH_4 prepared via direct synthesis method," *International Journal of Hydrogen Energy*, vol. 36, no. 17, pp. 10861–10869, 2011.
- [55] D. E. Mencer, T. R. Hess, T. Mebrahtu, D. L. Cocke, and D. G. Naugle, "Surface reactivity of titanium–aluminum alloys: Ti_3Al , TiAl , and TiAl_3 ," *Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films*, vol. 9, no. 3, pp. 1610–1615, 1991.
- [56] X. Zhang, Y. F. Liu, Z. H. Ren et al., "Realizing 6.7 wt% reversible storage of hydrogen at ambient temperature with non-confined ultrafine magnesium hydrides," *Energy & Environmental Science*, vol. 14, no. 4, pp. 2302–2313, 2021.
- [57] J. P. Perdew, K. Burke, and M. Ernzerhof, "Generalized gradient approximation made simple," *Physical Review Letters*, vol. 77, no. 18, pp. 3865–3868, 1996.
- [58] P. E. Blöchl, "Projector augmented-wave method," *Physical Review B*, vol. 50, no. 24, pp. 17953–17979, 1994.
- [59] G. Henkelman, B. P. Uberuaga, and H. Jónsson, "A climbing image nudged elastic band method for finding saddle points and minimum energy paths," *Journal of Chemical Physics*, vol. 113, no. 22, pp. 9901–9904, 2000.